

製品仕様一覧(GF-101~123)

下記の試験結果は測定値であり、保証値ではありません。

主な機能	品番	製品巾 (cm)	総厚 剥離紙除く (μm)	6mm厚フロートガラス貼付時									飛散 防止	UV カット	ハード コート	施工可能 なガラス	
				遮蔽係数	日射			可視光線		紫外線 透過 (%)	赤外線 透過 (%)	熱貫流率 (W/mK)					
					反射 (%)	透過 (%)	吸収 (%)	反射 (%)	透過 (%)								
透明フロートガラス(6mm厚)→				0.96	7	80	13	8	89	61	81	5.9	—	—	—	—	
透明 タイプ	透明断熱	GF-101	125	77	0.85	7	64	29	9	86	1未満	25	5.7	◎	●	●	透明
	飛散防止	GF-102-1	97	75	0.95	7	78	14	8	88	1未満	79	5.9	◎	●		透明 熱線遮蔽
		GF-102-2	125	75	0.95	7	78	14	8	88	1未満	79	5.9	◎	●		
	ハード コート	GF-103-1	97	77	0.95	7	78	14	8	88	1未満	79	5.9	◎	●	●	網入り
		GF-103-2	125	77	0.95	7	78	14	8	88	1未満	79	5.9	◎	●	●	
		GF-103-3	155	77	0.95	7	78	14	8	88	1未満	79	5.9	◎	●	●	
外貼り可	GF-104	97	125	0.94	9	77	15	10	86	1未満	79	5.9	◎	●			
日照調整 熱線遮蔽	GF-105-1	97	87	0.50	29	31	41	31	39	1未満	19	5.5	◎	●	●	透明	
	GF-105-2	97	52	0.50	30	31	39	31	39	1未満	19	5.5	◎	●	●		
	GF-106-1	97	87	0.31	45	15	40	51	19	1未満	16	5.5	◎	●	●		
	GF-106-2	97	52	0.31	46	15	39	51	19	1未満	16	5.5	◎	●	●		
外貼り可	GF-107	97	85	0.48	31	30	39	28	38	1未満	19	5.5	◎	●			
日照調整	GF-108	97	52	0.78	7	56	38	6	44	1未満	79	5.9	◎	●	●	透明	
	GF-109	97	52	0.69	6	43	50	5	19	1未満	79	5.9	◎	●	●		
	GF-110	97	52	0.77	7	54	39	5	39	1未満	79	5.9	◎	●	●		
	GF-111	97	52	0.67	6	42	48	5	17	1未満	79	5.9	◎	●	●		
サンド調	GF-112	97	75	0.96	8	74	18	9	85	1未満	74	5.9	◎	●		透明	
	GF-113	92	350	0.85	8	66	26	9	76	1未満	63	6.0	◎	●		熱線遮蔽	
	GF-114	92	350	0.83	7	63	30	7	70	1未満	63	6.0	◎	●		網入り	
	GF-115	92	350	0.83	7	63	29	8	71	1未満	63	6.0	◎	●		透明	
マット タイプ	GF-116	95	100	0.86	8	68	24	9	77	1未満	65	6.0	◎	●		透明 熱線遮蔽 網入り	
	GF-117	97	75	0.81	17	65	18	20	68	1未満	74	5.9	◎	●			
	GF-118	97	77	0.84	10	60	30	14	66	1未満	63	5.9	◎	●			
	GF-119	97	77	0.57	23	32	45	31	29	1未満	49	5.9	◎	●			
型板 ガラス調	GF-120	92	300	0.83	9	64	27	10	71	31	59	6.0	○			透明 熱線遮蔽 網入り	
	GF-121	93	400	0.88	9	71	29	11	77	14	67	6.0	○				
	GF-122	93	450	0.78	11	58	31	16	64	1未満	61	6.0	○				
	GF-123	93	450	0.77	10	57	33	11	57	3	59	6.0	○				